



## Marker Identification Tapes NEPTAPE® WM100P

**Construction:** 0.00092" (23μ) pigmented polyester film

**Description:** White pigmented polyester identification tape, printed with legend. Typically used in power cable applications.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0009 inches	23 microns	ASTM D374
Yield	150.0 ft <sup>2</sup> /lb. 0.56 lbs/mft @ 1" wide	30.7 m <sup>2</sup> /kg 0.33 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	17,400 psi	120 MPa	Calculated
Break Strength	16 lbs/in width	28 N/10mm width	ASTM D882
Elongation at Break	100%	100%	ASTM D882
Dielectric Strength of Film	4.0 kV	4.0 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	1.40 g/cm <sup>3</sup>	Calculated
Max. Continuous Operating Temperature	NA	NA	Supplier Data
Sealing Temperature	NA	NA	NEPTCO TM-008
Colors	White		
Splice Type	#24		
Standard Pad Put-ups	3" x 5,000'		
Standard Traverse Put-ups	NA		

\*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

**NEPTCO, Incorporated**  
 Box 2323, 30 Hamlet Street  
 Pawtucket, RI 02861-0323 USA  
 TEL: 401-722-5500  
 FAX: 401-722-6378