



Core Wrap / Separator Tapes

NEPTAPE® N96250

Construction: 0.00048” (12μ) polyester film
0.00400” (102μ) fiberglass scrim

Description: A flame retardant binder tape primarily used in the SEU and SER service entrance cables.

Typical Properties	US Customary	Metric	Test Method
Thickness	0.0045 inches (+/- 10%)	114 microns	ASTM D374
Yield	62.7 ft ² /lb. 1.33 lbs/mft @ 1" wide	12.8 m ² /kg 0.78 kg/km @ 10mm wide	NEPTCO TM-002
Tensile Strength	13,100 psi	90 MPa	Calculated
Break Strength	59 lbs/in width	103 N/10 mm width	ASTM D882
Elongation at Break	7%	7%	ASTM D882
Dielectric Strength of Film	2.8 kV	2.8 kV	Supplier Data
Dielectric Constant of Film	3.0 (dimensionless)	3.0 (dimensionless)	Supplier Data
Density	NA	0.68 g/cm ³	Calculated
Max. Continuous Operating Temperature	175°F	80°C	Supplier Data
Sealing Temperature	NA	NA	NEPTCO TM-008
Splice Type	#60, max. 6/pad		
Standard Pad Put-ups	Core ID - 3" or 6" Pad OD - 17"		

*ASTM Test Methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request.

The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Specification data can be provided upon request.

NEPTCO, Incorporated
Box 2323, 30 Hamlet Street
Pawtucket, RI 02861-0323 USA
TEL: 401-722-5500
FAX: 401-722-6378